

LISTSING OF THE CLAIMS

The following listing of claims will replace all prior versions and listings of claims in the application.

1. **(Previously Presented)** An electrochromic window comprising:
a first plate and a second plate disposed from said first plate, each of said first plate and said second plate being transparent to at least one wavelength of electromagnetic radiation;
a first electrically conductive layer and a second electrically conductive layer, said first electrically conductive layer being attached to said first plate and said second electrically conductive layer being attached to said second plate; and
a solid attenuation layer in the form of a single layer and disposed between said first electrically conductive layer and said second electrically conductive layer, said attenuation layer comprising an at least partially cured photopolymerizable monomer, an electrolyte and an electrochromic material, the photopolymerizable monomer bonding the electrolyte and electrochromic material to each other.
2. **(Original)** The electrochromic window of claim 1, wherein said first plate and said second plate comprise a glass.
3. **(Original)** The electrochromic window of claim 1, wherein said first conductive layer and said second conductive layer are transparent to at least one wavelength of electromagnetic radiation.
4. **(Original)** The electrochromic window of claim 1, wherein said photopolymerizable monomer comprises one of polymethylmethacrylate and methylpentene.
5. **(Original)** The electrochromic window of claim 1, wherein said attenuation layer attenuates electromagnetic waves that pass through said attenuation layer.
6. **(Canceled)**

7. **(Original)** The electrochromic window of claim 1, wherein said attenuation layer attenuates electromagnetic waves that pass through said attenuation layer based upon a voltage between said first electrically conductive layer and said second electrically conductive layer.

8. **(Previously Presented)** An electrochromic window comprising:
a first plate having an inside surface;
a second plate disposed from said first plate, said second plate having an inside surface;
an electrically conductive layer adjacent said inside surface of each of said first plate and said second plate; and

a solid attenuation layer in the form of a single layer and disposed between said first plate and said second plate, said attenuation layer comprising an electrochromic material, a guest-host electrolyte, and an at least partially curable photopolymerizable monomer, electrochromic material and said guest-host electrolyte being bonded to each other by the photopolymerizable monomer.

9. **(Original)** The electrochromic window of claim 8, wherein said first plate and said second plate comprise glass.

10. **(Original)** The electrochromic window of claim 8, wherein said first plate and said second plate are transparent to at least one wavelength of electromagnetic radiation.

11. **(Original)** The electrochromic window of claim 8, wherein the photopolymerizable monomer comprises one of polymethylmethacrylate and methylpentene.

12-15. **(Canceled)**

16. **(Withdrawn)** A method of manufacturing an electrochromic window comprising:

a step for positioning at least one conductive layer, said at least one conductive layer being configured to substantially transmit a particular wavelength of electromagnetic radiation;

a step for depositing an attenuation layer upon said at least one conductive layer, wherein said attenuation layer comprises an electrolyte material, an electrochromic layer, and an at least partially curable photopolymerizable monomer, said monomer being cured by a first wavelength of electromagnetic radiation; and

a step for transmitting said first wavelength of electromagnetic radiation, through said at least one conductive layer, to said attenuation layer to at least partially cure said monomer.

17. **(Withdrawn)** The method of claim 16, further comprising a step for positioning at least one plate adjacent to said at least one conductive layer.

18. **(Withdrawn)** The method of claim 16, further comprising a step for positioning at least one plate to receive said at least one conductive layer.

19. **(Withdrawn)** The method of claim 16, wherein said step for depositing said attenuation layer comprises:

a step for depositing a first layer comprising said electrolyte and said at least partially curable photopolymerizable monomer; and

a step for depositing a second layer upon said first layer, said second layer comprising said electrochromic material.

20. **(Withdrawn)** The method of claim 16, wherein said step for depositing said attenuation layer comprises:

a step for creating a solution of said electrolyte and said at least partially curable photopolymerizable monomer; and

a step for depositing a first layer, said first layer comprising said solution; and

a step for depositing a second layer upon said first layer, said second layer comprising said electrochromic material.

21. **(Withdrawn)** The method of claim 16, wherein said step for depositing said attenuation layer comprises:

- a step for creating a mixture of said electrolyte and said at least partially curable photopolymerizable monomer; and
- a step for depositing a first layer, said first layer comprising said solution; and
- a step for depositing a second layer upon said first layer, said second layer comprising said electrochromic material.

22. **(Withdrawn)** The method of claim 16, wherein said step for positioning said at least one conductive layer comprises applying a conductive liquid to at least one plate.

23. **(Withdrawn)** The method of claim 22, wherein said step for positioning said at least one conductive layer includes applying a solid sheet of conductive material upon at least one plate.

24. **(Withdrawn)** The method of claim 16, wherein the photopolymerizable monomer comprises one of polymethylmethacrylate and methylpentene.

25. **(Withdrawn)** A ROSA that includes the electrochromic window of claim 1, the ROSA further comprising:

- a preamp in electrical communication with the electrochromic window; and
- a photodiode in electrical communication with the preamp and in optical communication with the electrochromic window, the electrochromic window being arranged such that any optical signal received by the photodiode must first pass through the electrochromic window.

26. **(Withdrawn)** A header package that includes the ROSA of claim 25, the header package further comprising:

a cap having a window in optical communication with the electrochromic window;

a base member to which the cap is attached, the ROSA being positioned on the base member;

a pin extending into the base member and electrically connected to the preamp.

27. **(Previously presented)** The electrochromic window as recited in claim 1, wherein the photopolymerizable monomer bonds the attenuation layer to the first and second electrically conductive layers.

28. **(Previously presented)** The electrochromic window as recited in claim 8, wherein the photopolymerizable monomer bonds the attenuation layer to the electrically conductive layers.